

BLANK PAGE



Indian Standard SPECIFICATION FOR WILLOW CLEFTS FOR CRICKET BATS (First Revision)

UDC 674.031.623.22 : 674.038.3 : 685.635.84



@ Copyright 1985

INDIAN STANDARDS INSTITUTION
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 110002

Indian Standard

SPECIFICATION FOR WILLOW CLEFTS FOR CRICKET BATS

(First Revision)

Timber Sectional Committee, BDC 9

	•
Chairman	Representing
INSPECTOR GENERAL OF FORESTS	Ministry of Agriculture, New Delhi
Members	
Additional Chief Conservator of Forests	Forest Department, Government of Uttar Pradesh, Lucknow
ADDITIONAL INSPECTOR GENERAL OF FORESTS	Ministry of Agriculture, New Delhi
SHRI R. C. BEDI	Ministry of Defence (DGI)
Shri J. P. Bhardwaj (Alterna	
SHRI S. K. BANERJEE	National Test House, Calcutta
SHRI D. K. MANUNGO (Alterna	
	Himachal Pradesh Forest Department, Simla
Conservator of Forests (Al	
Shri V. N. Deshpande	Engineer-in-Chief's Branch, Army Headquarters, New Delhi
SHRI D. S. SAXENA (Alternate)	
DIRECTOR	Forest Department, Government of Karnataka, Bangalore
DIRECTOR	Indian Plywood Industries Research Institute, Bangalore
DIRECTOR (TRACKS)	Railway Board (Ministry of Railways)
JOINT DIRECTOR (CE) (TM)	
DR RAMESH DAYAL	Forest Research Institute & Colleges (Wood
	Anatomy Branch), Dehra Dun
EDITOR	National Buildings Organization, New Delhi
Industrial Adviser	Directorate General of Technical Development,
	New Delhi
SHRI P. V. MEHTA (Alternate)	
Shri U. B. Kanchan	R & D Organization (Ministry of Defence), New Delhi
SHRI B. B. MEHTA (Alternate)	
SHRI K. L. LAULY	Federation of Indian Plywood and Panel Industry, New Delhi

(Continued on page 2)

© Copyright 1985

EXECUTIVE DIRECTOR (Alternate)

INDIAN STANDARDS INSTITUTION

This publication is protected under the *Indian Copyright Act* (XIV of 1957) and reproduction in whole or in part by any means except with written permission of the publisher shall be deemed to be an infringement of copyright under the said Act.

(Continued from page 1)

•	•		
л.	1en	nha	* 0

Representing

DR A. N. NAYAR

personal capacity (C-59, Inderpuri, Ďelhi)

SHRI R. C. PRASAD

Bihar State Forest Development Corporation

SHRI B. M. PRASAD (Alternate) PRESIDENT

Limited, Patna

New

DR SATISH KUMAR (Alternate)

Indian Academy of Wood Science, Dehra Dun Indian Plywood Manufacturing Co Ltd, Bombay

DR A. PURUSHOTHAM CAPT MOHAN RAMAN Naval Headquarters, New Delhi

COR MANMOHAN SINGH (Alternate)

Forest Research Institute and Colleges (Timber SHRI S. S. RAJPUT

DR V. RANGANATHAN

Mechanics Branch), Dehra Dun In personal capacity (28-C, N Block, Malviya Nagar Extension, Saket, New Delhi)

SHRI A. C. SEKHAR

personal capacity (17-1-391/54, Subramanya Colony, Saidabad, Hyderabad)

SHRIF, C. SHARMA SHRI SHARAN SINGH Directorate General of Civil Aviation, New Delhi Directorate General of Supplies and Disposals,

DR M. C. TEWARI

New Delhi Forest Research Institute & Colleges (Forest Products Department), Dehra Dun

DR A. CHANDRA (Alternate) SHRI G. RAMAN, Director (Civ Engg)

Director General, ISI (Ex-officio Member)

Secretary

SHRI P. SATYANARAYANA Assistant Director (Civ Engg), ISI

Timber Conversion and Grading Subcommittee, BDC 9: 10

Convener

SHRI A. C. SEKHAR 17-1-391/54, Subramanya Colony, Saidabad, Hyderabad

CONSER- Forest Department, Government of Uttar Pradesh, CHIEF Additional Nainital VATOR OF FORESTS

CONSERVATOR OF FORESTS (Alternate)

Ministry of Defence (DGI) SHRI R. C. BEDI

SHRI J. P. BHARDWAJ (Alternate) CHIEF CONSERVATOR OF FORESTS Agriculture Forests and Co-operation Department, Government of Gujarat, Vadodara

ADDITIONAL CHIEF CONSER-VATOR OF FORESTS (Alternate)

(Continued on page 6)

Indian Standard SPECIFICATION FOR WILLOW CLEFTS FOR CRICKET BATS (First Revision)

0. FOREWORD

- 0.1 This Indian Standard (First Revision) was adopted by the Indian Standards Institution on 28 February 1985, after the draft finalized by the Timber Sectional Committee had been approved by the Civil Engineering Division Council.
- 0.2 The supply of willow clefts used for cricket bats is of great economic and technical importance for the sports goods industry. This standard was first published in 1967 with a view to provide guidance to the suppliers and purchasers in regard to the requirements for willow clefts suitable for cricket bats. With the publication of IS: 828-1979* need was felt to revise this standard. As such this revision has been taken up wherein, all species of willow permitted in IS: 828-1979* have been included and mechanical strength requirements of willow clefts have been modified.
- 0.3 For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS: 2-1960†. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

1. SCOPE

1.1 This standard lays down the requirements of willow clefts for use in the manufacture of cricket bats.

2. TERMINOLOGY

2.1 For the purpose of this standard, the definitions given in IS: 707-1976; shall apply.

^{*}Specification for cricket bats (second revision).

[†]Rules for rounding off numerical values (revised).

[‡]Glossary of terms applicable to timber technology and utilization (second revision).

3. SPECIES OF TIMBER

3.1 The following species of timber shall be used:

Botanical Name

Trade Name

Abbreviated Symbol

Salix spp.

Willow

WIL

4. GENERAL REQUIREMENTS

4.1 Seasoning — The cleft shall be seasoned according to IS: 1141-1973*.

Note — The clefts are generally air seasoned.

- 4.2 Moisture Content The moisture content of the cleft shall be not less than 8 percent and not more than 12 percent. Moisture content shall be determined in accordance with 4 of IS: 1708-1969†. The specimen used for determination of moisture content shall be a disc of thickness 2.5 cm taken at least 10 cm away from the ends of the clefts.
- **4.3 Density** The density of the timber at 12 percent moisture content shall not be less than 400 kg/m^3 and not more than 550 kg/m^3 .
- **4.3.1** For moisture content below 12 percent, the value of density specified in **4.3** shall be computed by decreasing the same at the rate of 2 kg/m³ for each 1 percent decrease in moisture content from 12 percent.
- 4.4 Straightness of Grains The clefts shall be smooth and of straight grain. The maximum inclination of the grain, spiral or diagonal to the length of the clefts shall not exceed 1 in 20.
- 4.5 Size The length of clefts shall be about 70 cm. However, smaller sizes may also be accepted for small size bats. The clefts shall have an approximately triangular cross-section with base about 12.5 cm and the other sides about 10 cm each or they may be roughly semi-circular with base width of about 12.5 cm.
- **4.6 Defects** Clefts shall be free from sapwood, gum, veins, spongy heart or other forms of rot, shakes and splits, loose grain gelatinous fibres, compression wood and pitch pockets.
- 4.6.1 Occasional pin holes and fine drying checks are, however, permissible.
- 4.6.2 No knot shall be permitted on the face and the edges of the cleft. Knots up to 15 mm may be permitted on the back of the cleft provided they are not very near the edge. Knots in clusters are also not permitted.

^{*}Code of practice for seasoning of timber (first revision).

[†]Methods of testing small clear specimens of timber (first revision).

4.7 Ring Width — The width of the growth rings on the cross-section shall be between 3 and 8 mm.

5. MECHANICAL STRENGTH REQUIREMENTS

5.1 The mechanical strength requirements of willow wood for the clefts shall not be less than the values specified in Table 1. Mechanical properties given in Table 1 shall be determined in accordance with IS: 1708-1969*.

TABLE 1 MECHANICAL STRENGTH REQUIREMENTS OF WILLOW WOOD FOR THE CLEFTS

St No.	Characteristic	STRENGTH VALUE
i)	Fibre stress (FS) at limit of proportionality (LP)	23 N/mm^2
ii)	Equivalent fibre stress at maximum load (modulus of rupture)	49 N/mm ²
iii)	Modulus of elasticity	$44 \times 10^2 \mathrm{N/mm^2}$
iv)	Work up to limit of proportionality	$0.6 \times 10^{-2} \mathrm{N/mm^3}$
v)	Hardness radius or tangential (Indentation test)	2 500 N
vi)	Toughness or brittleness (Izod test)	150 mm/N

6. MARKING

- 6.1 Each willow cleft shall be marked in a suitable manner with the manufacturer's identification mark or initials.
- 6.1.1 Each willow cleft may also be marked with the ISI Certification Mark.

Note — The use of the ISI Certification Mark is governed by the provisions of the Indian Standards Institution (Certification Marks) Act and the Rules and Regulations made thereunder. The ISI Mark on products covered by an Indian Standard conveys the assurance that they have been produced to comply with the requirements of that standard under a well-defined system of inspection, testing and quality control which is devised and supervised by ISI and operated by the producer. ISI marked products are also continuously checked by ISI for conformity to that standard as a further safeguard. Details of conditions under which a licence for the use of the ISI Certification Mark may be granted to manufacturers or processors, may be obtained from the Indian Standards Institution.

^{*}Methods of testing small clear specimens of timber (first revision).

(Continued from page 2)

Members

Representing

CHIEF CONSERVATOR OF FORESTS Forest Department, Government of Himachal Pradesh, Simla

CONSERVATOR OF FORESTS (Alternate)

CHIEF CONSERVATOR OF FORESTS Forest Department, Government of West Bengal, Calcutta

CONSERVATOR OF FORESTS (Alternate)

DIRECTOR (TRACKS) Railway Board (Ministry of Railways)

JOINT DIRECTOR (Alternate)
DR R. GHANAHARAN Kerala Forest Research Institute, Peechi

Directorate General of Technical Development, INDUSTRIAL ADVISER New Delhi (CHEMICALS)

SHRI P. V. MEHTA (Alternate)

U.P. Forest Corporation, Lucknow Managing Director

REGIONAL MANAGER (Alternate)

Himachal Pradesh State Forest Corporation Ltd, MANAGING DIRECTOR Simla

OFFICER-IN-CHARGE Forest Research Institute & Colleges (Logging Branch), Dehra Dun

Directorate General of Civil Aviation, New Delhi SEE P. C. SHARMA SHRI R. T. SOMAIYA Bombay Timber Merchants Association Limited, Bombay

SHRI JIMMY WADIA (Alternate)



INDIAN STANDARDS INSTITUTION

Tolograme · Manakeanstha

6 27 16

Headquarters:

	n to all Offices)
Regional Offices:	Telephone
*Western: Manakalaya, E9 MIDC, Marol, Andheri (East BOMBAY 400093), 6 32 92 95
†Eastern : 1/14 C. I. T. Scheme VII M, V. I. P. Road. Maniktola, CALCUTTA 700054	36 24 99
Southern : C. I. T. Campus, MADRAS 600113	41 24 42
Northern: B69 Phase VII, Industrial Focal Point, S. A. S. NAGAR 160051 (Punjab)	8 73 28
Branch Offices:	
'Pushpak', Nurmohamed Shaikh Marg, Khanpur, AHMADABAD 380001	{2 63 48 2 63 49
'F' Block, Unity Bldg, Narasimharaja Square. BANGALORE 560002	22 48 05

Manak Bhavan, 9 Bahadur Shah Zafar Marg, NEW DELHI 110002

24 04 24 2 24 12 75

BHOPAL 462003 22E Kalpana Area, BHUBANESHWAR 751014 5 36 27 5-8-56C L. N. Gupta Marg, HYDERABAD 500001 22 10 83 R14 Yudhister Marg, C Scheme, JAIPUR 302005 6 98 32

117/418 B Sarvodaya Nagar, KANPUR 208005 4 72 92
Patliputra Industrial Estate, PATNA 800013 6 23 05
Hantey Bldg (2nd Floor), Bly Station Road, 32 27

Hantex Bldg (2nd Floor), Rly Station Road, TRIVANDRUM 695001

Gangotri Complex, Bhadbhada Road, T. T. Nagar,

Inspection Office (With Sale Point):

Institution of Engineers (India) Building, 1332 Shivaji Nagar. 5 24 35 PUNE 410005

[•]Sales Office in Bombay is at Novelty Chambers, Grant Road, 89 65 28 Bombay 400007 †Sales Office in Calcutta is at 5 Chowringbee Approach, P. O. Princep 27 68 00 Street, Calcutta 700072